

Technical Data Sheet

LDPE/PP regranulate natural
Product Code: 230202



Description

This LDPE/PP regranulate comes from post-industrial recycling PIR and was recovered in Europe. It is suitable for injection moulding applications.

General Properties	Value	Standard
MFR	19-25 g/10min	EN ISO 1133 230°C/2.16kg
Bulk density	545 kg/m ³	
Density	0,98 g/cm ³	EN ISO 1133
E-Modulus	1070 Mpa	EN ISO 527-7/2
Yield Stress	22 Mpa	EN ISO 527-7/2
Strechting Elongation	8%	EN ISO 527-7/2
Tear resistance	16 Mpa	EN ISO 527-7/2
Elongation at break	27%	EN ISO 527-7/2

NOTICE:

All properties are current, typical data of the stated product. All statements, data and information given herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.