

Technical Data Sheet

PIR LDPE Regranulate natural transparent

Product Code: 013505



Physical Properties	Value	Units	Test Method
Physical state	Solid granules	1	/
Color	Natural, clear to translucent	1	1
Density	0.94	g/cm³	ISO 1183-1
MFI (190°C/ 2,16kg)	0.3-07	g/10 min	ISO 1133-1
Ash content	1-3	%	ISO 3451-1:1997

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.

Handelsregisternummer: HRB 33699, Amtsgericht Bremen Ust-IdNr: DE319539787 Geschäftsführer: Marvin Pfeiffer Bankverbindung Deutsche Bank IBAN: DE68 2907 0050 0211 0799 00 BIC: DEUTDEHBXXX