

Bankverbindung

Deutsche Bank

BIC: DEUTDEHBXXX

DE68 2907 0050 0211 0799 00

IBAN:

Technical Data Sheet

PIR LDPE Regranulate natural transparent

Product Code: 081301



| Physical Properties | Value | Units | Test Method |
|---------------------|-------------------------------|----------|-----------------|
| Physical state | Solid granules | 1 | / |
| Color | Natural, clear to translucent | | 1 |
| Density | 0.94 | g/cm³ | ISO 1183-1 |
| MFI (190°C/ 2,16kg) | 0.4 | g/10 min | ISO 1133-1 |
| Ash content | 1-3 | % | ISO 3451-1:1997 |

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.