

# Technical Data Sheet

PCR PP Recompound Black ESD Electrically Conductive

Product Code: 013806



Physical Properties	Value	Units	Test Method
Density	1,01	g/cm <sup>3</sup>	ISO 1183
MFR (230°C/2,16kg)	20	g/10 min	ISO 1133
<b>Mechanical Properties</b>			
Tensile Modulus	1250	MPa	ISO 527
Tensile Stress At Yield	22	MPa	ISO 527
Elongation At Yield	20	%	ISO 527
Charpy Impact Strength, Unnotched	n.b.	kJ/m <sup>2</sup>	ISO 179 1eU 23°C
Charpy Impact Strength, Notched	15	kJ/m <sup>2</sup>	ISO 179 1eA 23°C
<b>Electrical Properties</b>			
Surface Resistance	<10 <sup>3</sup>	Ohm	IEC 61340-2-3

## Application

Electrically conductive injection moulded parts of different kinds of application.

## Technical Data Sheet

### Processing

Injection Moulding

Predrying: 80°C/2-4 h

Working Temperature: 200-260°C

Tool Temperature: 40-60°C

### Delivery Form

Will be delivered as pellets or cylinder granules with a cutting length of approx. 3 mm in Polyethylen valve sacks with 25 kg, aluminium covered sacks with 25 kg, in Octabins, BigBags or silo trucks.

### Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.