

Technical Data Sheet

PCR PP Regranulate

Product Code: 000604

Description

PCR PP 000604 is a 100% PCR (post-consumer recycled) polypropylene material with a good melt flow rate and good tensile and flexural strength, designed for injection molding process. **PCR PP 000604** is made from 100% PCR products, including food boxes, water cups and drinking water bottles, these products are manufactured through high quality recycling process, consist of hot washing, melt filtration, pelletization and degassing etc., comply with GRS (Global Recycled Standard) and food contact materials (FCM) regulations.

Applications	
Food Containers	Packaging components
Lids	Water cups
Children toys	Houseware containers

Special Features		
Lower impurity content c	ontrol	Stable MFR suitable for injection molding

Compliance	
BPA Free	FDA compliant
REACH (224 SVHC)	RoHS Directive (EU) 2011/65
California Prop. 65	ТРСН
EU Regulations EC No 1935/2004 & EU No 10/2011	

Physical Properties	Value	Units	Test Method
Density	0,9	g/cm^3	ISO 1183
MFI (230°C/ 2,16kg)	9	g/10 min	ISO 1133
Tensile Stress (50mm/min)	30	MPa	ISO 527-2

Sinox Polymers GmbH Grünenweg 5-7 DE-28195 Bremen info@sinox-polymers.com +49 178 / 8175 168 Handelsregisternummer: HRB 33699, Amtsgericht Bremen Ust-IdNr: DE319539787 Geschäftsführer: Marvin Pfeiffer, Kai Michael Pfeiffer Bankverbindung Deutsche Bank IBAN: DE68 2907 0050 0211 0799 00 BIC: DEUTDEHBXXX



Technical Data Sheet

Flexural Modulus	1300	MPa	ISO 178
Flexural Strength	35	MPa	ISO 178
Ash Content	0,8	%	ISO 3451-1
Melt Point	160	°C	ISO 11357
Molding Shrinkage	1,6	%	Internal
Charpy Impact Strength, unnotched (23°C)	97	KJ/m^2	ISO 180
Charpy Impact Strength, notched (23°C)	3,5	KJ/m^2	ISO 180
Heat Deflection Temperature (0,45MPa)	91	°C	ISO 75-2
Heavy Metals (Rohs)	Cd, Hg, Pb, Cr	-	

Processing Conditions

PCR PP 000604 is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature:	180 -210 °C
Holding pressure:	200 – 500 bar
Mould pressure:	60-100 MPa
Mould temperature:	30-50 °C
Molding time:	30-60 s

Shrinkage 1 - 2%, depending on wall thickness and moulding parameters.

Handelsregisternummer: HRB 33699, Amtsgericht Bremen Ust-IdNr: DE319539787 Geschäftsführer: Marvin Pfeiffer, Kai Michael Pfeiffer



Technical Data Sheet

Storage

PCR PP 000604 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odor generation and color changes and can have negative effects on the physical properties of this product.

More information on storage can be found in Material Safety Data Sheet (MSDS) for this product.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Disclaimer

This information contained herein is based on the data available to us and is believed be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy these data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.

Handelsregisternummer: HRB 33699, Amtsgericht Bremen Ust-IdNr: DE319539787 Geschäftsführer: Marvin Pfeiffer, Kai Michael Pfeiffer Bankverbindung Deutsche Bank IBAN: DE68 2907 0050 0211 0799 00 BIC: DEUTDEHBXXX