

Technical Data Sheet

PP Regranulate natural color

Product Code: 014809



Description

This natural colored PP regranulate comes from Post Industrial Recycling PIR and was recovered in Europe. It is suitable for injection moulding applications.

Physical Properties	Value	Units	Test Method
Density	0.92	g/cm ³	DIN 53479
MFR (230°C/2.16kg)	3.2	g/10 min	DIN ISO 1133-1
Tensile strength	30-35	N/mm ²	DIN EN ISO 527
Elongation at Break	>50	%	DIN EN ISO 527
E-Module	1400-1515	N/mm ²	DIN EN ISO 527
Notched impact strength (23°C)	5.5	kJ/m ²	DIN EN ISO 179, 1eA
Ash content	0.1	%	DIN EN ISO 1172

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.