

Technical Data Sheet

PP Regrind

Product Code: 013003



General Properties	
Color	Mixed colored
Form	regrind
Composition	Post Consumer Recycling
Certification	EuCertPlast

Properties	Value	Units	Standard
MFI (230°C/ 2,16kg)	21,9	g/10 min	ISO 1133-A
Density	0,917	g/ml	ISO 1183-1A
DSC Analysis	PP: 96 PE: 4	%	ISO 11357
Traction	25,8	MPa	ISO 527-2 type 1A 23°C / 50 mm/ min.
Elasticity modulus (tensile)	1100	MPa	ISO 527-2 type 1A 23°C / 1 mm/ min.
Fracture rotation	6,6	%	ISO 527-2 type 1A 23°C / 50 mm/ min.
Charpy (+23/ 1e)	39,4	kJ/m ²	ISO 179 / 1
Charpy notched (+23/ 1eA)	4,5	kJ/m ²	ISO 179 / 1

Packaging
Big bags on pallets

Technical Data Sheet

NOTICE:

All properties are current, typical data of the stated product. All statements, data and information given herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

