

# Technical Data Sheet

PVC Regranulate White Color

Product Code: 300501



## Description

PVC from white colored window profile and pipe waste material. For extrusion applications.

General Properties	Value	Standard
Density	1.52-1.55 g/cm <sup>3</sup>	ISO 1183
VICAT B50 - softening point	77-81 °C	EN ISO 306
Thermostability	20 Minutes	EN ISO 179-1
Charpy Impact Strength at 23°C	3-7 kJ/m <sup>2</sup>	DIN 53381-C

### NOTICE:

All properties are current, typical data of the stated product. All statements, data and information given herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.